

InCorr 2238

Corrosion inhibitor

Properties

- Highly concentrated and therefore economical to dose
- Temporary corrosion inhibitor for steel (low alloyed or non-alloyed)

Application

InCorr 2238 is a concentrate for the preparation of passivation baths.

Instructions for use:

Allow surfaces treated with InCorr 2238 to air dry. Avoid rinsing and moisture ingress! Avoid exposure to acids, especially hydrochloric acid. Check the pH value of the application solution regularly (target: pH value 8 - 9). Treat surfaces that are as optically clean as possible (surface impurities, e.g. rust deposits or pigment soiling interfere with the formation of the passivation layer). Avoid direct exposure to moisture (rain etc.). The corrosion passivation layer is moderately water-soluble. Prolonged exposure to moisture therefore leads to its dissolution.

Suitable surfaces: Steel (low-alloy or non-alloy)

Not suitable surfaces: Non-ferrous metals and zinc tend to darken; no passivation of aluminum and aluminum alloys

Dosing

Dipping or Spraying Process

| | |
|---------------|---------------|
| Concentration | 2 % – 10 % |
| Temperature | 56 °C – 70 °C |

Technical data

| Density (20°C) | pH-value |
|----------------|----------|
| 1,05 kg / l | 8 - 9 |

Notes

Store the product only in the original container and frost-free.

For commercial use only. This leaflet is for non-binding information only. The information is based on our current knowledge and experience. In any case, the user is obliged to carry out his own tests and trials to check the suitability of the products for his intended processes and purposes. The information in this leaflet does not constitute a guarantee for the quality and durability of the goods to be supplied by us. We reserve the right to make technical changes within the scope of what is reasonable. The current version of the corresponding EU safety data sheet must also be observed.