

Terasit AP

Impregnating agent



Properties

- air-permeable fabric impregnation
- excellent abrasion resistance
- free of organic halogen compounds including fluorocarbon compounds
- also suitable for tents, tarpaulins and heavy fabrics

Application

Terasit AP should be applied in the dip-roller process as the last rinsing bath in a washer extractor. Terasit AP should only be added after the liquor level has been reached and the drum movement has started.

Terasit AP is applied in a single bath. Before impregnation, the cleaned textiles must be thoroughly rinsed to remove all detergent and alkali residues, as even small amounts of surfactants or detergents can lead to a deterioration in the effect. It is advisable to add approx. 1 ml / l acetic acid 60% to the last rinsing bath to ensure that the goods no longer contain alkali. Terasit AP is diluted with 3 - 5 times its volume of water at 30 - 50 °C while stirring. High shear forces should be avoided, as the emulsion can be irreversibly damaged.

This stock solution is then added to the treatment liquor while stirring. The treatment bath is adjusted with acetic or formic acid to pH 4 - 5.

30 - 40 ml/l are required to impregnate garments. For materials that are difficult to wet, the liquor temperature can be increased to 50°C. The normal temperature is between 20 and 40 °C. The goods are treated in the impregnation bath for 20 - 30 min, briefly spun, dried (attention: observe care label!) and ironed as usual (iron approx. 150 °C). For large pieces of fabric (tent and carriage covers), the impregnation can be carried out by applying a 40 - 60 ml / l Terasit AP solution to the fabric using a spray gun, brush, sponge or roller. When working with standing baths, the initial concentration must be added when the liquor level is replenished (30 - 40 ml / l).

Technical data

Density (20°C)	pH-value
1,00 kg / l	3,5 - 4,5

Notes

Store the product only in its original container and in a frost-free place.

The product should not be stored below 0°C or above 40°C.

Irreparable damage is possible.

For commercial use only. This leaflet is for non-binding information only. The information is based on our current knowledge and experience. In any case, the user is obliged to carry out his own tests and trials to check the suitability of the products for his intended processes and purposes. The information in this leaflet does not constitute a guarantee for the quality and durability of the goods to be supplied by us. We reserve the right to make technical changes within the scope of what is reasonable. The current version of the corresponding EU safety data sheet must also be observed.