

# Secasit Lotus

Fabric protection finishes and impregnating agents



## Properties

- excellent water, oil and dirt repellent
- a protective film envelops each individual fiber to protect the fabric
- does not affect the breathability of the fabric
- high wearing comfort, soft handle and elegant shine

## Application

Application quantity: at least 30 - 40 ml Secasit Lotus per kg of fabric. Secasit Lotus is used only by spraying. Depending on the installed spraying system, the calculated amount is sprayed on in concentrated form or a spray solution is used consisting of one part Secasit Lotus and 4 - 6 parts perchloroethylene. The spraying time should be at least 3 minutes. No spinning before the drying cycle necessary. Before the blower is switched on, allow to roll for 3 - 5 min, dry for 10 min at 50 °C and then increase the temperature to 65 °C.

## Special instructions

The spray method may only be used inside the machine. Inhaling the aerosols is strongly discouraged!

## Technical data

### Density (20°C)

1,30 kg / l

## Notes

Store the product only in its original container and in a dry place.

Highly concentrated FC resin solutions may become cloudy at temperatures below 5°C. They do not lose their effectiveness. The processing temperature should be > 10°C.

For commercial use only. This leaflet is for non-binding information only. The information is based on our current knowledge and experience. In any case, the user is obliged to carry out his own tests and trials to check the suitability of the products for his intended processes and purposes. The information in this leaflet does not constitute a guarantee for the quality and durability of the goods to be supplied by us. We reserve the right to make technical changes within the scope of what is reasonable. The current version of the corresponding EU safety data sheet must also be observed.