

# SECASENE Lotus

Fabric protection finish and impregnating agent

SENSENE™

## Properties

- specially adapted to the properties of SENSENE™
- excellent water, oil and dirt repellent
- does not affect the breathability of the fabric
- high wearing comfort, soft handle and elegant shine

## Application

Application quantity: 40 ml/kg goods

Secasene Lotus is only applied by spraying. The calculated quantity is sprayed on in concentrated form. Secasene Lotus can be sprayed onto either spin-dried or dried goods. To achieve a good impregnating effect, the fabric should be well cleaned and rinsed. The spraying time should be at least 3 minutes. Intermediate spinning before drying is not necessary. Before the blower is switched on, the fabric should be left to roll for at least 5 minutes. A high drying temperature improves the impregnation effect.

Impregnation on machines with Jet-Clean technology

Load: 50 - 70 %

Application rate: 40 ml/kg

Recommendation: The nozzle should be rinsed after spraying. Roll for 5 minutes after spraying.

To avoid loading the system with excess impregnating agent, a full impregnation batch should only be run once a day. In addition, the drum regeneration with subsequent rinsing program must be carried out in a warm state (e.g. at the end of the day). For drum regeneration, we recommend using cotton mix cloths (approx. 6 m<sup>2</sup> in total) to ensure optimum removal of impregnation residues. The cloths can be reused after they have been washed.

## Special instructions

The spraying process may only be used inside the machine. We urgently warn against inhaling the aerosols!

## Technical data

Density (20°C)
0,82 kg / l

## Notes

Store the product only in the original container and in a dry place.

Highly concentrated FC resin solutions can become cloudy below 5°C. They do not lose their effect.

They do not lose their effect. The processing temperature should be > 10°C.

For commercial use only. This leaflet is for non-binding information only. The information is based on our current knowledge and experience. In any case, the user is obliged to carry out his own tests and trials to check the suitability of the products for his intended processes and purposes. The information in this leaflet does not constitute a guarantee for the quality and durability of the goods to be supplied by us. We reserve the right to make technical changes within the scope of what is reasonable. The current version of the corresponding EU safety data sheet must also be observed.